



# Update on tests with passive strucutres on CHESS 2 chip

ATLAS Strip CMOS meeting, 10.01.2017

Bojan Hiti et al.

Jožef Stefan Institute, Experimental Particle Physics Department (F9) Ljubljana, Slovenia



Resistivity	Wafer	Wafers	Number
$[\Omega\text{-cm}]$	numbers	cut	of cut chips
std	1-6	1, 2	94
50-100	7-12	7, 8	97
200-300	13-18	13, 14	94
600-2000	19-24	19, 20	95




Neutron fluences 0e14, 1e14, 3e14, 5e14, 1e15, 2e15 neq/cm2

#### Test structures:

- 3 x 3 pixel array for E-TCT (pixel size 630 x 40 μm<sup>2</sup>)
- Large array for Sr90 measurements (1.2 x 1.2 mm²)

#### Sr90 measurements





Collected charge is less than expected from E-TCT measurements

#### But is that really the case?


Calibration of the Q-TCT setup was carried out, discussion on next slides

## Q-TCT calibration 1



#### Sr90 calibration procedure

- using epitaxial diodes with known thickness (d = 50 and 100  $\mu$ m)
- after epi-layer is fully depleted extract scaling factor  $A = d \times 100$  pairs/ $\mu$ m /  $V_{sig}$



Only n-type diodes could be biased highly enough for calibration p-type breaks down at 60 V, before full depletion


#### Q-TCT calibration 2



#### **Results:**

calibration factor in the same range as used up to now  $A = 275\,000$  pairs / V, but

the signals for unirradiated CHESS 2 devices are actually what we would expect only irradiated CHESS 2 devices have less charge than expected:




Depleted depth for CHESS 2 is determined from the formula: (N eff from E-TCT)

$$d = \sqrt{\frac{2\varepsilon\varepsilon_0}{e_0 N_{\text{eff}}} V_{\text{bias}}}$$

## Sr90 Comparison for different substrates






CHESS1 vs. CHESS2 (std. resistivity) : trend is similar, but mean charge differs Could be due to a different wafer composition  $\rightarrow$  different acceptor removal

#### Top TCT



- Charge from Sr90 measurements systematically only 60 % of that expected for the depletion depth measured by E-TCT
- Investigate with top TCT
  - IR light 980 nm, abs. depth 100  $\mu$ m  $\rightarrow$  no reflections from back plane



W19 5e14
Big array for Sr90
(1.2 mm x 1.2 mm)

Gaps between pixels due to metalization on top of the chip


But on the large scale intensity in central pixels less than on edges!

#### Top TCT 2



Difference in the collected charge indicates a larger depletion depth on the edges of the Sr 90 array.


Edge-like pixels also measured in Edge-TCT. This may be a reason for discrepancy between the measurements.



CCE at y=585 µm

# W13 unirradiated (200 Ohm-cm), $\lambda$ =980 nm







Unirradiated sample:

For 100 V bias charge is uniform across the structure, while for 10 V bias there is a distinctive gap in the centre. However the gap can be recovered by increasing integration time (next slide)


## W13 unirradiated (200 Ohm-cm), $\lambda$ =980 nm







CCE at V bias = 10 V



1000

800

t int = 50 ns

In unirradiated samples the non-uniformity is recovered by increased integration time (.

What about irradiated samples?

CHESS 2 passive structures


10.01.2017

300

200

## Pulses shape unirradiated 10 V bias






# W19 5e14 n/cm2 (2 kOhm-cm), $\lambda$ =980 nm



12




Neutron irradiation 5e14 n/cm2, wafer 19 (other than unirradiated sample)

Hole in the center remains for all integration times

Bojan Hiti (IJS) CHESS 2 passive structures 10. 01. 2017

#### Pulse shape irradiated sample





Pulse shape does not change with position, only the scaling changes

Possible explanations:

- Different depleted depth
- Different light absorption (why?)

Bojan Hiti (IJS)

CHESS 2 passive structures

10. 01. 2017

#### Summary




- Missing charge in Sr90 measurement
  - Before irradiation the collected charge is compatible with other measurements
  - After irradiation less charge is collected than expected / in other measurements
- Investigation with top TCT:
  - The centre of the Sr array collects less charge than the edges
  - Before irradiation: difference depends on integration time
  - After irradiation: difference depends much less on integration time
- Conclusions at present:
  - Charge collection within the Sr90 array is not uniform
  - Possible reasons:
    - Different depletion depth
    - Different light absorption
    - Electrical bugs?
    - Any ideas ?
- Further investigations TBD



# **BACKUP**

#### Passive structures on CHESS2






**Red traces** - metalization



#### Neff vs. fluence



$$\left| N_{\text{eff}} = N_{\text{eff0}} - N_{c} \cdot (1 - \exp(-c \cdot \Phi_{\text{eq}})) + g_{c} \cdot \Phi_{\text{eq}} \right|$$




Removal at the highest resistivity substrate is completed below 1e14 neq/cm2 and was not observed in this study

should verify again

#### Acceptor removal constant vs. doping




18



#### I-V characteristic






I-V measured on a TCT array (3 x 3 pixels, pixel size 630 x 40  $\mu$ m<sup>2</sup>)

## E-TCT Charge collection profiles W1




20



- Moderate charge collection width, but increases with irradiation
- Low resistivity → late acceptor removal

#### Charge collection width vs. fluence





20 Ohm-cm: late acceptor removal, largest charge collection region at highest measured fluences

$$Width(V_{\text{bias}}) = w_0 + \sqrt{\frac{2\varepsilon\varepsilon_0}{e_0 N_{\text{eff}}}} V_{\text{bias}}$$


Extract value from fit

#### N<sub>eff</sub> vs. fluence




Fit: 
$$N_{\rm eff} = N_{\rm eff0} - N_{\rm c} \cdot (1 - \exp(-c \cdot \Phi_{\rm eq})) + g_c \cdot \Phi_{\rm eq}$$
 acceptor removal

Radiation introduced deep acceptors








#### Depletion depth W19








$$Width(V_{\text{bias}}) = w_0 + \sqrt{\frac{2\varepsilon\varepsilon_0}{e_0 N_{\text{eff}}} V_{\text{bias}}}$$

 Sqrt functions falling monotonously with fluence

#### Sr90 charge




25



- TCT 1e14: depletion zone 120 um at 100 V
- We still collect less charge than expected (f.e. meas. 7000 e vs. 12000 e expected)
- Investigate with top TCT ?

#### Sr90 spectra W19







### Charge profiles W7, W13




• Edge-TCT charge collection profile across central pixel





• increase of width with fluence up to 1e15

#### W13 (200 $\Omega$ ·cm)




not much change of profile width with fluence

## REMINDER Depletion depth W7, W13




width of charge collection profile vs. bias

W7 (50  $\Omega$ ·cm)



W13 (200  $\Omega$ ·cm)



Fit: 
$$Width(V_{\text{bias}}) = w_0 + \sqrt{\frac{2\varepsilon\varepsilon_0}{e_0 N_{\text{eff}}}} V_{\text{bias}}$$

At  $\Phi = 0$ 

- W7:  $N_{eff} = 2.3e14 \text{ cm}^{-3}$   $\rightarrow$  56  $\Omega \cdot \text{cm}$
- W13:  $N_{eff} = 6.6e13 \text{ cm}^{-3}$
- **→** 200 Ω·cm


→ Good fit, good agreement with nominal resistivity

#### REMINDER Sr90 W7, W13




29






#### W13 (200 $\Omega$ ·cm)



- large drop of collected charge (delta ≈ 1300 el) after first irradiation step to 1e14 n/cm2
  - → reduced contribution from diffusion
- TCT measurements indicate depleted region > 50 μm
  - Expect > 5000 el. from drift
  - Measure 2000 el.

#### IV-curves wafer 13





No IV curves for wafer 7 due to a bug, but 0e14, 1e14, 1e15, 2e15 OK up to 120 V 5e14 up to 110 V, 3e14 at least up to 90 V


#### High resistivity wafers



31

- After suggestion from Santa Cruz tried biasing the substrate from other pads:
  - a & d → breakdown at 18 V
  - a & b → breakdown at 18 V
  - c & d → breakdown at 1 V
  - c & b → breakdown at 1 V

Planning also to measure IV of irradiated devices on probe station to see if there is improvement after irradiation



a – LPA nwells

b – LPA substrate

c – Large Pad


nwells


d – Large Pad substrate


Bojan Hiti (IJS) CHESS 2 passive structures 10. 01. 2017


#### Profiles W19 1e14






























#### Profiles W19 3e14






























#### Profiles W19 5e14






























#### Profiles W19 1e15


























#### Profiles W19 2e15



